

**Engineered Thermoplastic Composite Reinforced
with Kevlar® Aramid Fiber.
The Ultimate Stock Shape for Wear and Abrasion Resistant Parts.**

HYDLAR'S TOP FEATURES OFFER:

- Superior Wear Resistance
- Virtually No Abrasion to Counter Surfaces
- High Use Temperature
- Greatly Improved Mechanical Properties
- Outstanding Machinability
- High P.V. Limit

**EXCLUSIVE WEAR AND ABRASION
RESISTANT PROPERTIES**

HYDLAR possesses a combination of physical properties that cannot be found in any other commercially available product. Using HYDLAR composites, design engineers have created a new family of superior wear and abrasion resistant thermoplastics to choose from.

THE COST-EFFECTIVE ANSWER

Now it's possible to achieve low abrasiveness without sacrificing low wear rates. Ordinary thermoplastic composites achieve low wear rates by using a reinforcement that adds to their strength and/or stiffness. But most, however, also show correspondingly high abrasiveness to counter

surface. HYDLAR thermoplastic composites are the exception. HYDLAR's tough, strong reinforcing material makes the end product extremely wear resistant without excessive galling to mating wear surface (see below). In addition HYDLAR improves mechanical properties and increases surface temperature capabilities.

THREE GRADES AVAILABLE**HYDLAR Z**

(NYLON/KEVLAR COMPOSITE)

HYDLAR ZT

(NYLON/KEVLAR/TEFLON COMPOSITE)

Provides increased wear and lubricity.

HYDLAR ZM

(NYLON/KEVLAR/MOLYBDENUM DISULPHIDE COMPOSITE) Offers improved surface hardness, increased wear and lubricity.

YOUR PARTNER

A. L. Hyde's applications development team can be a valuable partner in your search for new and better materials to use in high-temperature, heavy-wear situations. We would be happy to apply our knowledge to your product and market needs. Contact your local Hyde distributor or call Hyde at **1-800-234-4933**.

HYDLAR

High-Strength Rods and Slabs

| HYDLAR Z | Test Units | Injection Molded & Extruded | | | Molded Only | Extruded & Molded |
|---|-----------------------|-----------------------------|---------------------------|------------------------|------------------------|------------------------|
| | | Nylon* 6/6 | Nylon*** 6 | Nylon* 6/6 | Nylon* 6/6 | HYDLAR Z 6/6 |
| Fiber | — | None | Glass | Glass | Glass | Nylon/Kevlar |
| Content | % | —0— | 10% | 13% | 33% | N/A |
| Tensile Strength | PSI x 10 ³ | 12.0 | 14.0 | 15.0 | 27.0 | 16.0 |
| Tensile Modulus | PSI x 10 ⁶ | — | .9 | — | — | 1.3 |
| Elongation | % | 60.0 | 3.2 | 2.0 | 3.0 | 4.0 |
| Flexural Strength | PSI x 10 ³ | — | 18.0 | — | — | 23.0 |
| Flexural Modulus | PSI x 10 ⁶ | .41 | .6 | .7 | 1.3 | .9 |
| Notched Izod Impact | Ft.-lb./in. | 1.0 | 1.1 | .9 | 2.0 | 2.7 |
| Compressive Strength | PSI x 10 ³ | 13.0 | 14.5 | — | 24.0 | 19.3 |
| Test Distortion Temp @ 264 PSI | ° F | 194A | 370 | 470 | 480 | 470 |
| Continuous Use Temp [‡] | ° F | 210 | 200 | 210 | 230 | 300 |
| Coefficient of Linear Thermal Expansion | in / in / °F | 4.0 x 10 ⁻⁵ | — | 1.5 x 10 ⁻⁵ | 1.3 x 10 ⁻⁵ | 1.6 x 10 ⁻⁵ |
| Specific Gravity Water Absorption 24 hrs | gr / cm ³ | 1.14 | 1.21 | 1.22 | 1.38 | 1.16 |
| Immersion 73° F | % | 1.2 | — | — | .7 | .8 |
| Saturation 73° F | % | 8.5 | — | 7.1 | 5.4 | 6.3 |
| Wear Factor*** | — | 867 to 1105 | 149-Melting of Nylon 6 | N/A | 424 | 128 to 79 |
| Galling of Mating Test Surface | — | Minor | Heavy | — | Severe | None |

‡ Depending on PV *DuPont Zytel Property Charts except wear **RTP Test Data except wear ***ASTM Thrust Washer Test: PV = 2,500 P= 250PSI V = 10 f.p.m.

We believe this information is the best currently available on the subject. It is subject to revision as additional knowledge and experience are gained. A.L. Hyde Company makes no guarantee of results and assumes no obligation of liability whatsoever in connection with this information. Anyone intending to use recommendations contained in this publication should first satisfy himself that the recommendations are suitable for his use and meet all appropriate safety and health standards. This publication is not a license to operate under, or intended to suggest infringement of any existing patents. References to products not of A.L. Hyde manufacture do not indicate endorsement of named products or unsuitability of other similar products.

For more information contact A.L. Hyde Company, or your local distributor of Hyde quality engineering thermoplastics.

Your local distributor:

ALH03695

HYDE

A. L. HYDE COMPANY

1 Main Street
Grenloch, New Jersey 08032
609-227-0500 Fax: 609-232-1754
1-800-234-HYDE (4933)
Industrial Plastics Since 1932